

TEST, UNIT OF MEASURE

RESULTS

REQUIREMENTS

Flame Resistance
(NFPA 701-2010)

Test Method 2 – Flat Configuration

Char Length, inches

8.6
8.3
8.6
8.6
8.4
8.4
8.1
8.4
8.4
8.7

Average:

8.5

17.1 Maximum

Drippings and flaming, seconds

0.0
0.0
0.0
0.0
0.0
0.0
0.0
0.0
0.0
0.0

Average:

0.0

2.0 Maximum

The sample tested above **meets** the requirements outlined in **Chapter 15 of NFPA 701-2010, Test Method 2.**

I certify that the above tests were performed under my supervision in accordance with the specification test requirements and that the reported test results are true, valid and applicable to the samples tested. I further certify that these samples are the only samples tested from the lot of components identified above.

Signed 
Edward L. Magill Jr.
President